

PROPERTY ⁽¹⁾	TEST METHOD	FREQUENCY	UNIT Metric	1084470
SPECIFICATIONS				
Average Thickness (Range)	ISO 9863-1	Every roll	mm	1.50 - 1.59
Thickness (min.)	ISO 9863-1	Every roll	mm	1.42
Density (min.)	ISO 1183-1	Every 10 rolls	g/cm ³	0.940
Carbon Black Content	ASTM D4218	Every 10 rolls	%	2.0 - 3.0
Carbon Black Dispersion (10)	ASTM D5596	Every 15 rolls	Category	Cat. 1 & Cat. 2
OIT - Standard (200°C; Pure O ₂ ; 1 atm)	ISO 11357	Every 60 rolls	min	100
Puncture Resistance	NFP 84-507	Every 10 rolls	N	495
Puncture Displacement	NFP 84-507	Every 10 rolls	mm	13.6
Tensile properties (MD/CMD)	EN 12311-2	Every roll		
Strenght at Yield			kN/m	24.3
Elongation at Yield			%	10.0 - 13.6
Strength at 250% Elongation			kN/m	17.1
Dimensional Stability (MD/CMD)	DIN 53377	Every 10 rolls	%	± 2
Stress Crack Resistance	EN 14576	Every 200 rolls	hr	500
SUPPLY SPECIFICATIONS(Roll dimensions may vary ±1%)				
Roll Dimension - Width	-		m	7.50
Roll Dimension - Length	-		m	140.0
Area (Surface/Roll)	-		m ²	1050.00

NOTES

1. Testing frequency based on standard roll dimensions.

10. Dispersion only applies to near spherical agglomerates. 9 of 10 views shall be category 1 or 2.

* All values - unless otherwise noted - are minimum values.

* The information contained herein is provided for reference purposes only and is not intended as a warranty or guarantee. Final determination of suitability for use contemplated is the sole responsibility of the user. SOLMAX assumes no liability in connection with the use of this information.

Solmax is not a design professional and has not performed any design services to determine if Solmax's goods comply with any project plans or specifications, or with the application or use of Solmax's goods to any particular system, project, purpose, installation or specification.